



## GENERAL PRODUCT SPECIFICATION

<b>Item No.</b>	MRO15-E
-----------------	---------

<b>Date</b>	03-31-08	<b>Replaces</b>	05-31-06	<b>No. Pages</b>	1
-------------	----------	-----------------	----------	------------------	---

### Product Description:

<b>Style</b>	Blanket Roll
<b>Item Size (each)</b>	38 cm wide by 46 m long
<b>Color</b>	Gray
<b>Composition</b>	Polypropylene >98%, Surfactant < 1.0%, color pigment < 0.1 %
<b>Structure</b>	96% natural white meltblown nonwoven fibers(<10 microns) 4% white spunbond nonwoven coverstock(<15-30 microns)
<b>Technology</b>	Meltblown + spunbond
<b>Absorbency</b>	Universal ( <b>Hydrophilic</b> + Oleophilic)
<b>Bonding</b>	Bonded (staggered pattern) + Mechanical entanglement

<b>Intended Application</b>	Low -Lint Chemical Resistant Sorbent for Water, Oil, or Solvent Base Liquids
-----------------------------	--

<b>Absorbency Capacity</b>	94 l per bale (saturated; medium viscosity-12.5x)
----------------------------	---

### Packaging Description:

Package configuration	Case	Pkg. Weight	7.5 kg (6.4 kg)
Items per Package	1-Roll/Case	Pkg. Dimensions	46cm x46cm x 40cm H
Container type	Carton		

### Physical Properties:

Parameter	SPC Test Method	Units	Nominal	(+/-)Tolerance
Basis Weight	SPCTM-002A	G/M2	365	37
Caliper	SPCTM-020	mm	5.3	0.5
Absorbency** (med. Oil)	SPCTM-004B	gL/gS	12.5	2
Tensile Strength	SPCTM-007	daN	14	1.4
Color	Visual	-----	Gray	per standard

The above properties are “nominal” values used for **PROCESS CONTROL** when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

\*\* The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

<b>Attributes</b>	Product will be free of foreign material contamination, rips, holes, and tears.
<b>Labeling</b>	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
<b>Certification</b>	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.

SPC International, Atealaan 71, I.Z. Klein Gent, B-2200 Herentals, Belgium  
Tel +32(0)14 321855 Fax +32(0)14 320440