



**GENERAL PRODUCT SPECIFICATION**

<b>Item No.</b>	<b>MS40-8</b>
-----------------	---------------

<b>Date</b>	6-29-06	<b>Replaces</b>	New	<b>No. Pages</b>	1
-------------	---------	-----------------	-----	------------------	---

**Product Description:**

<b>Style</b>	SOC
<b>Item Size (each)</b>	7.6 cm d x 244 cm long
<b>Color</b>	Gray with red logo printing
<b>Composition</b>	Super absorbent polymer
<b>Structure</b>	<u>Sorbent fill:</u> Super absorbent polymer <u>Outer covering:</u> Spunbond polypropylene nonwoven (15-30 micron dia. fiber)
<b>Technology</b>	Meltblown + Spunbond + Sealed or Enclosed Ends
<b>Absorbency</b>	<b>Hydrophilic</b> + Oleophilic

<b>Intended Application</b>	“Universal” Sorbent Sock for Non-Aggressive Spills of Water Base, Oil Base, or Solvent Base Liquids
-----------------------------	---

<b>Absorbency Capacity</b>	130 l per case (saturated; medium viscosity- 12.5x)
----------------------------	---

**Packaging Description:**

Package configuration	Case	Pkg. Weight	10.8 kg (9.0 kg)
Items per Package	15 SOCS/Case	Pkg. Dimensions (approx.)	64.5 cm x 43.5 cm x 54 cm
Container type	Carton		

**Physical Properties:**

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
SOC Weight	Gravimetric	kg	0.6	0.06
Absorbency** (med. oil)	SPCTM-012B	gL/gS	12.5	11-min.
Color	Visual	-----	Gray	per standard

The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

\*\* The "Absorbency" Spec and "SPCTM012" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

<b>Attributes</b>	Product will be free of foreign material contamination, rips, holes, and tears.
<b>Labeling</b>	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
<b>Certification</b>	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.

SPC International, Atealaan 71, I.Z. Klein Gent, B-2200 Herentals, Belgium  
Tel +32(0)14 321855 Fax +32(0)14 320440