



GENERAL PRODUCT SPECIFICATION

Item No.	UXT315-P-E
-----------------	-------------------

Date	03-31-08	Replaces	06-12-06	No. Pages	1
-------------	----------	-----------------	----------	------------------	---

Product Description:

Style	Blanket Roll; high strength perforation every 46 cm for single or multiple/variable length pads
Item Size (each)	38 cm wide by 46 m long (100 Pads)
Color	Dark Gray
Composition	Polypropylene >98%, Surfactant < 1.0%, color pigment < 0.1 %
Structure	A nonwoven mat where the middle ply is made of randomly oriented Micro-fibers [2-10 micron diameters] and the coverstock layers are lint-resistant & abrasion resistant {controlled porosity} spunbond nonwoven of continuous filaments randomly oriented and thermally point bonded [15-30 micron diameters].
Technology	Meltblown & Spunbond, 3-ply
Absorbency	Universal (Hydrophilic + Oleophilic)
Bonding	Bonded (staggered pattern) + Mechanical entanglement

Intended Application	Low -Lint Chemical Resistant Sorbent for Water, Oil, or Solvent Base Liquids
-----------------------------	------------------------------------------------------------------------------

Absorbency Capacity	70 l. per bale (saturated; medium viscosity-13.5x)
----------------------------	----------------------------------------------------

Packaging Description:

Package configuration	Case	Pkg. Weight	6.6 kg (5.1kg)
Items per Package	1 Roll / Case 100 pads	Pkg. Dimensions	43cm x 43cm x 40cm H
Container type	Carton		

Physical Properties:

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
Basis Weight	SPCTM-002A	G/M2	290	29
Caliper	SPCTM-003A	mm	4.6	0.5
Absorbency ** (med. Oil)	SPCTM-004B	gL/gS	13.5	2
Tensile Strength	SPCTM-006	daN	12.7	1.3
Color	Visual	-----	Dark Gray	per standard

The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

**** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.