

Date 05	5-04-07	Replaces	11-15-06		No. Pages	1
---------	---------	----------	----------	--	-----------	---

Product Description:

Style	Barrier Backed, Blanket Roll
Item Size (each)	1.52m x 46m
Color	Gray on White
Composition	Polypropylene >98%, Surfactant < 1.0%, color pigment < 0.1 %
Structure	Three ply roll. The bottom barrier layer is a white, spunbond nonwoven, treated with a 25μ thick film. The middle layer is a gray meltblown nonwoven sorbent comprised of micro-fiber [2-10 micron diameters] mechanically entangled. The top layer is gray spunbond coverstock.
Technology	Meltblown, 3-ply
Absorbency	Hydrophilic + Oleophilic
Bonding	Bonded (staggered pattern) + Mechanical entanglement

Intended Application	Low -Lint Chemical Resistant Barrier Sorbent Blanket Roll for Water, Oil or
	Solvent Base Liquids

Absorbency Capacity	291 l (saturated; medium viscosity-10x)

Packaging Description:

Package configuration	Bale	Package Weight (net weight)	26.3 kg (25.2 kg)
Items per Package	1 Roll / Bale	Package Dimensions	43cm x 43cm x
			155cm
Container type	Polybag + Twist Tie		

Physical Properties;

<u>Parameter</u>	SPC Test Method	<u>Units</u>	Nominal	(+/-)Tolerance
Basis Weight	SPCTM-002A	G/M2	360	36
Caliper	SPCTM-003A	mm	4.8	0.48
Absorbency** (med.	SPCTM-004B	gL/gS	10	2
Oil)				
Tensile Strength	SPCTM-007	daN	18.6	1.8
Color	Visual		Gray/White	per standard

The above properties are "nominal" values used for PROCESS CONTROL when the product is produced and/or inspected. Performance "nominals" may vary depending upon the specific application, and/or the environment being applied, stored, or shipped. ** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.			
Labeling	Each package to be clearly labeled with Company Name, Address, Item No.,			
Lasting	Date, and/or Package Code (Bar Code).			
Certification	Make no changes in basic process or composition without notifying customer.			
	Claims for non-conformance of goods must be made within 60-days of delivery.			