



HIGH PERFORMANCE VpCI® COATINGS

VpCI® -384



PRODUCT DESCRIPTION

VpCI-384 is a two-part urethane top coat designed to be used over a moisture cure urethane primer, such as VpCI-396. VpCI-384 can be prepared in almost any color desired. The major advantage this top coat offers is excellent adhesion to a moisture cure urethane even after it is fully cured. In addition, VpCI-384 has a high gloss, excellent hardness, extremely good flexibility, excellent solvent resistance, and does not contain aromatic solvents.

FEATURES

- Excellent adhesion to moisture cure urethanes even when fully cured
- High gloss
- Excellent flexibility
- Excellent solvent resistance
- Very hard coating

METALS PROTECTED

- Steel
- Aluminum
- Cast iron
- Galvanized steel

TYPICAL APPLICATIONS

- Bridges
- OEM
- Structural steel
- Tanks

TYPICAL PROPERTIES

Appearance	Liquid, various colors
Induction time	30 minutes
Dry time	6 to 8 hours at room temperature
Cure time	7 days at room temperature
Flash point	73°F (23°C)
Non-volatile content	50-70% by weight (45-68% by volume)
Shelf life	1 year
Pot life	3 to 4 hours
Theoretical spread rate	268-537 ft ² /gal at 2-4 mils (6.7-13.4 m ² /l at 50-100 microns)
Viscosity	30-40" (#2 Zahn cup)*
VOC (Regulatory)	2.7- 2.8 lb/gal
Mixed	(324-336 lb/gal)
VOC (Actual)	2.7-2.8 g/l
Mixed	(324-336 g/l)
Density	8.9-11.0 lb/gal (1.07-1.32 kg/l)
Adhesion	5B
Film Hardness	6H+ pencil hardness

*can vary per color



SURFACE APPLICATION

Stir VpCI-384 prior to usage. VpCI-384 is designed to be applied over a urethane primer. The ideal time to apply the top coat is when the primer is just tack free. VpCI-384 can, however, be applied after the primer has cured without any significant drop in adhesion. VpCI-384 should not be applied directly to metal.

Normal wet film thickness of 3-6 mils (75-150 microns) yields 2-4 mils (50-100 microns).

Methods for Monitoring Application:
Wet film thickness gauge.

Product Cleanup:
Butyl acetate, acetone, MEK

PACKAGING AND STORAGE

VpCI -384 is available in 5 gallon (1.9 liter) kits: 4 gallons (15.2 liters) of Part A in a 5 gallon metal pail and a one gallon (3.8 liters) can of Part B.

VpCI -384 Aluminum is available in 6 gallon (22.8 liter) kits: 5 gallons (19 liters) of Part A in a 5 gallon metal pail and a one gallon (3.8 liters) can of Part B.

LIMITATIONS

After mixing Part A and Part B, wait for 30 minutes before applying VpCI-384. Air temperatures should be between 20°F and 100°F (-7°C and 38°C).

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT SAFETY DATA SHEET FOR MORE

INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



Distributed by:

4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@corotecvci.com
Internet <http://www.corotecvci.com>

printed on recycled paper  100% post consumer
Revised: 8/7/13. ©Cortec Corporation 2004-2013. All rights reserved. Supersedes: 5/12/11.
© 2013, Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. ISO accreditation applies to Cortec's processes only.